

Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with patent application GB0327067.5 filed on 21 November 2003.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.


In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed




Dated 9 September 2008



The Patent Office

21NOV03 E853892-1 002914  
P01/7700 0.00-0327067.5



The Patent Office

Cardiff Road  
Newport  
South Wales  
NP9 1RH

# Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference

MSP642

0327067.5

2. Patent application number

(The Patent Office will fill in this part)

21 NOV 2003

3. Full name, address and postcode of the or of each applicant (underline all surnames)

DOW CORNING CORPORATION  
Midland  
Michigan 48611  
USA

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

USA/Michigan

8506640002

4. Title of the invention

POLYMERIC PRODUCTS USEFUL AS OIL REPELLENTS

5. Name of your agent (if you have one)

P V Davies

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

DOW CORNING LIMITED  
Intellectual Property Department  
Cardiff Road  
Barry  
CF63 2YL

Patents ADP number (if you know it)

44037001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number  
(if you know it)

Date of filing  
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing  
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
  - b) there is an inventor who is not named as an applicant, or
  - c) any named applicant is a corporate body.
- See note (d))

Yes

**Patents Form 1/77**

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 15

Claim(s) 3

Abstract

Drawing(s)

RM

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

1

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

1 fee sheet

11.

I/We request the grant of a patent on the basis of this application.

Signature

P V Davies

Date

20/11/2003

12. Name and daytime telephone number of person to contact in the United Kingdom

P V Davies 01446 723505

**Warning**

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

**Notes**

- a) If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- b) Write your answers in capital letters using black ink or you may type them.
- c) If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- d) If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- e) Once you have filled in the form you must remember to sign and date it.
- f) For details of the fee and ways to pay please contact the Patent Office.

POLYMERIC PRODUCTS USEFUL AS OIL REPELLENTS

[0001] This invention relates to polymeric products suitable for application to fibrous substrates such as textiles, leather and paper, to impart oil (oleophobicity) and water repellent (hydrophobicity) properties to the treated material, and to the preparation of the polymeric products.

[0002] Fluorocarbon polymers are extensively used in the textile industry to impart oleophobicity/oil repellency to a fabric. For example, US-A-5247008 describes finishing agents for textiles, leather, paper and mineral substrates which are aqueous dispersions of a copolymer of a perfluoroalkyl acrylate or methacrylate, an alkyl acrylate or methacrylate and an aminoalkyl acrylate or methacrylate.

[0003] US-A-5068295 describes a water and oil repellent comprising a copolymer of a perfluoroalkyl acrylate or methacrylate, a polyorganosiloxane containing a vinyl group and a vinyl monomer containing an isocyanate or blocked isocyanate group.

[0004] US-A-6582620 and US-A- 5883185 describe a treating composition for textiles to render them water and oil repellent obtained by cohydrolysis and condensation of (A) a fluorinated alkyl-bearing alkoxysilane, (B) an amino-bearing alkoxysilane, and (C) an alkoxysilyl-bearing polyorganosiloxane.

[0005] US-A-5536304 describes application of a blend of a succinic anhydride-terminated polydimethylsiloxane and a poly(fluoroalkyl methacrylate) to cotton to give a fabric with oil repellency.

[0006] US-A-6472019 describes treating a textile with a water- and oil-repellent agent comprising a fluorine-containing polymer and a sulfated fatty acid compound.


[0007] One of the major disadvantages of topical finishes prepared with fluorocarbon polymers is that they impart a harsh feel to the fabric surface. There is a need for textile treatment agents which impart oleophobicity and oil repellency to fabrics without imparting a

harsh feel to the fabric surface, and preferably whilst at the same time imparting an improvement in feel compared to untreated fabric.

[0008] A polymeric product according to the invention having oil repellent properties comprises an amino-functional polysiloxane (A) bonded through its amino groups to an addition copolymer (B) of (B1) a fluoro-substituted alkyl ester of an olefinically unsaturated carboxylic acid and (B2) an olefinically unsaturated monomer having a functional group capable of reacting with the amino groups of polysiloxane (A) and optionally (B3) one or more olefinically unsaturated comonomers.


[0009] The invention includes a process for the preparation of a product having oil repellent properties in which an amino-functional polysiloxane (A) is reacted with an addition copolymer (B) of (B1) a fluoro-substituted alkyl ester of an olefinically unsaturated carboxylic acid and (B2) an olefinically unsaturated monomer having a functional group capable of reacting with the amino groups of polysiloxane (A) and optionally (B3) one or more olefinically unsaturated comonomers.

[0010] The amino-functional polysiloxane (A) is preferably a polydiorganosiloxane containing aminoalkyl groups attached to silicon. The aminoalkyl groups can be terminal groups to the polydiorganosiloxane and/or pendant to the polydiorganosiloxane chain. The amino groups are preferably primary or secondary amino groups and the aminoalkyl groups are preferably of the formula



wherein A and A' are each independently a linear or branched alkylene group having 1 to 6 carbon atoms; q = 0-4; and R is hydrogen or an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms. Most preferably R is hydrogen; q = 0 or 1; and A and A' (if present) each contain 2 to 4 carbon atoms. Examples of preferred aminoalkyl groups include  $-(CH_2)_3NH_2$ ,  $-(CH_2)_4NH_2$ ,  $-(CH_2)_3NH(CH_2)_2NH_2$ ,  $-CH_2CH(CH_3)CH_2NH(CH_2)_2NH_2$ ,  $(CH_2)_3NHCH_2CH_2NH(CH_2)_2NH_2$ ,  $-CH_2CH(CH_3)CH_2NH(CH_2)_3NH_2$ ,  $(CH_2)_3NH(CH_2)_4NH_2$  and  $-(CH_2)_3O(CH_2)_2NH_2$ .


[0011] For many functional group-containing monomers (B2), the amino-functional polysiloxane (A) can contain tertiary amino groups. The aminoalkyl groups attached to silicon can be of the formula




- 5 where A, A', q and R are defined as above and each R' is hydrogen or an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms.

[0012] The groups attached to silicon other than aminoalkyl groups are generally optionally substituted alkyl, aryl or aralkyl groups and are preferably alkyl groups having 1 to 4 carbon atoms, most preferably methyl groups. The polysiloxane is preferably linear but can be branched, for example it can contain branching units such as  $CH_3SiO_{3/2}$  units, but such branching units preferably form no more than 5 mole% of the polysiloxane.

[0013] The amino-functional polysiloxane used in the invention can for example be of the formula



where A, A', R and q are defined as above and x is for example 4-1000, or may have the formula



where A, A', R and q are defined as above; Y is an optionally substituted alkyl or aryl group; Z and Z', which can be the same or different, are each an optionally substituted alkyl, aryl or aralkyl group; X is hydrogen or an aliphatic group, preferably an alkyl group having 1 to 30, particularly 6 to 20, carbon atoms, or a triorganosilyl group such as trimethylsilyl; m is for example 4-1000; and n is for example 1-1000, preferably 2-100. The preparation of such amino-functional polysiloxanes is described in WO-A-03/16380.

[0014] The copolymer (B) is generally produced by addition polymerisation of the fluoro-substituted alkyl ester (B1) of an olefinically unsaturated carboxylic acid with the olefinically unsaturated monomer (B2) having a functional group capable of reacting with the amino groups of polysiloxane (A) and optionally with one or more olefinically unsaturated comonomers. (B3). The olefinically unsaturated carboxylic acid is preferably acrylic or methacrylic but can alternatively be maleic, fumaric or itaconic acid.









[0015] The fluoro-substituted alkyl ester monomer (B1) is preferably an acrylate or methacrylate ester of the formula  $\text{CH}_2=\text{C}(\text{R}'')\text{COO-D-Rf}$  or  $\text{CH}_2=\text{C}(\text{R}'')\text{COO-Rf}$ , where Rf is a branched or linear fluoroalkyl group having 3 to 21 carbon atoms, R'' is H or methyl, and D is a divalent organic group. D may for example be a linear or branched alkylene group having 1 to 20 carbon atoms, for example a group of the formula  $-(\text{CH}_2)_x-$  where x is 1 to 10, a group of the formula  $-\text{SO}_2\text{N}(\text{R}^1)\text{R}^2-$  or of the formula  $-\text{CON}(\text{R}^1)\text{R}^2-$ , where R<sup>1</sup> is an alkyl group having 1 to 10 carbon atoms and R<sup>2</sup> is a linear or branched alkylene group having 1 to 10 carbon atoms, or a group of the formula  $-\text{CH}_2\text{CH}(\text{OR}^3)\text{CH}_2-$  where R<sup>3</sup> represents a hydrogen atom or an acyl group having 1 to 10 carbon atoms such as formyl or acetyl, or a group of the formula  $-\text{Ar-CH}_2-$  where Ar is an arylene group optionally having a substituent.

[0016] Specific examples of the fluoro-substituted alkyl ester monomer (B1) are

20  $\text{CF}_3(\text{CF}_2)_7(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$   
 $\text{CF}_3(\text{CF}_2)_7(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$   
 $\text{CF}_3(\text{CF}_2)_7(\text{CH}_2)_{10}\text{OCOCH}=\text{CH}_2$   
 $\text{CF}_3(\text{CF}_2)_7(\text{CH}_2)_{10}\text{OCOC}(\text{CH}_3)=\text{CH}_2$   
 $\text{CF}_3(\text{CF}_2)_6\text{CH}_2\text{OCOCH}=\text{CH}_2$

25  $\text{CF}_3(\text{CF}_2)_8\text{CH}_2\text{OCOCH}=\text{CH}_2$   
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_6(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$   
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_8(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$   
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_{10}(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$   
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_6(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$

30  $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_8(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$   
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_{10}(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$   
 $\text{CF}_3(\text{CF}_2)_9(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$



Esters with a relatively long chain perfluoroalkyl moiety such as heptadecafluorodecyl may be preferred as because they have been widely used in the past to give good oil repellency, or esters with a relatively short chain perfluoroalkyl moiety such as nonafluorohexyl may be preferred as being less persistent in the environment. The fluoro-substituted alkyl ester monomer (B1) can if desired be a perfluoroalkyl acrylate or methacrylate such as nonafluorohexyl methacrylate or acrylate.

20

[0017] The olefinically unsaturated monomer (B2) which is copolymerised with (B1) is preferably a substituted alkyl acrylate or methacrylate ester wherein the substituent in the alkyl group is a functional group capable of reacting with the amino groups of polysiloxane (A). The most preferred functional group for reacting with the amino groups is epoxide. The monomer (B2) can for example be glycidyl methacrylate or acrylate. The amino-functional polysiloxane (A) can thus be bonded to the copolymer (B) by  $-\text{N}(\text{R})-\text{CH}_2-\text{CHOH}-$  linkages derived from reaction of the amino groups of (A) with epoxide groups in the copolymer (B), where R is hydrogen or an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms.

25

30 [0018] If the amino groups in the amino-functional polysiloxane (A) are tertiary amino groups, the amino-functional polysiloxane (A) may be bonded to the copolymer (B) by quaternary ammonium-containing linkages derived from reaction of the tertiary amino groups



of (A) with epoxide groups in the copolymer (B), such as  $-N^+(R)(R')-CH_2-CHOH-$  linkages or by reaction with carboxyl groups present in copolymer (B).

[0019] The functional group capable of reacting with the amino groups of polysiloxane (A) can alternatively be an anhydride, imide, lactone, carboxylic acid, isocyanate or blocked isocyanate group. Anhydride groups react with amino groups to form an amide linkage. Examples of olefinically unsaturated monomers having an anhydride functional group are maleic anhydride and itaconic anhydride. Imide groups react with amino groups to form an amide linkage. An example of an olefinically unsaturated monomers having an imide functional group is maleimide. Lactones react with amino groups to form an amidic ester linkage. Carboxylic acid groups react with amino groups, which can be tertiary, secondary or primary amino groups, at temperatures below about 100°C to form an ionic salt linkage, and at temperatures above about 100°C react with primary or secondary amine groups to form an amide linkage. Examples of olefinically unsaturated carboxylic acids are acrylic acid, methacrylic acid and maleic acid.

[0020] The addition copolymer (B) optionally includes units derived from one or more olefinically unsaturated comonomers. (B3). Examples of such olefinically unsaturated comonomers include alkyl acrylate or methacrylate esters having 1 to 30 carbon atoms in the alkyl group such as butyl acrylate, ethyl acrylate, methyl acrylate, methyl methacrylate or butyl methacrylate. The alkyl acrylate or methacrylate can be used to adjust the glass transition temperature ( $T_g$ ) of the copolymer (B); for example an acrylate having a long chain alkyl group of 4-20, particularly 8-20 carbon atoms such as stearyl acrylate or methacrylate, octyl acrylate, 2-ethylhexyl acrylate or dodecylacrylate or methacrylate can be used to form a softer polymer of lower  $T_g$ . Copolymers with an alkyl acrylate or methacrylate monomer may improve various properties such as water- and oil- repellency and soil releasability, cleaning durability, washing durability and abrasion resistance of such repellency and releasability, solubility in solvent, hardness and feel (handle). Other acrylate or methacrylate comonomers (B3) which can be used are polyethylene glycol acrylate or methacrylate, polypropylene glycol acrylate or methacrylate, methoxypolyethylene glycol acrylate or methacrylate and methoxypolypropylene glycol acrylate or methacrylate, Other olefinically unsaturated comonomers (B3) which can be used are vinyl chloride, vinylidene chloride,

styrene, acrylonitrile, methacrylonitrile, ethylene, a vinyl alkyl ether, isoprene or a vinyl ester such as vinyl acetate or vinyl propionate. An olefinically unsaturated comonomer (B3) can be used which contains a functional group that, although not reactive with amine groups, may be reactive with other functional groups to give properties such as increased substantivity on  
 5 textiles and other substrates. Examples of such functional groups are hydroxyl, amino and amide, and examples of olefinically unsaturated comonomers (B3) containing them are acrylamide, methacrylamide, N-methylolacrylamide, hydroxyethyl methacrylate, hydroxyethyl acrylate, 3-chloro-2-hydroxypropyl acrylate or methacrylate, N,N-dimethylaminoethyl acrylate or methacrylate and diethylaminoethyl acrylate or methacrylate.

10 [0021] The addition copolymer (B) can be prepared by free radical polymerisation of the monomers, preferably in solution, for example in a polar organic solvent such as one or more alcohol, ketone or ester solvents selected from butanol, t-butanol, isopropanol, butoxyethanol, methyl isobutyl ketone, methyl ethyl ketone, butyl acetate or ethyl acetate  
 15 and/or an aromatic hydrocarbon such as xylene, toluene or trimethylbenzene a blend of one or more of these. The initiator for free radical polymerisation is preferably an azo compound such as azobisisobutyronitrile or azoisovaleronitrile (AIVN) but can be a peroxide such as benzoyl peroxide. The polymerisation temperature can for example be in the range 50-120°C.

20 [0022] The reaction between the amino-functional polysiloxane (A) and the addition copolymer (B) is preferably carried out in solution, for example in a polar organic solvent as described above. The reaction can conveniently be carried out by adding the amino-functional polysiloxane (A) to a solution of addition copolymer (B), for example the solution  
 25 resulting from polymerisation. The reagents are usually heated to effect reaction. The preferred temperature of reaction depends on the nature of the functional group in monomer (B2) which reacts with the amino groups of polysiloxane (A). When the functional group is an epoxide group, for example when monomer (B2) is glycidyl methacrylate, the preferred temperature of reaction is generally in the range 60-120°C.

30 [0023] The amino-functional polysiloxane (A) and the addition copolymer (B) can be reacted in various proportions. For example the amino groups of (A) may be present in

stoichiometric excess over the functional groups derived from monomer (B2), forming a polymeric product having residual unreacted amino groups. Such a polymeric product may be preferred for greater substantivity to fibrous substrates or softness of handle of the treated material. Alternatively the polysiloxane and the addition copolymer can be reacted in approximately stoichiometric amounts of amino groups of (A) and functional groups derived from monomer (B2), or the functional groups derived from monomer (B2) may be present in stoichiometric excess over the amino groups of (A), forming a polymeric product bearing substantially no residual unreacted amino groups. Such a polymeric product may be preferred for maximum hydrophobicity.

**[0024]** The polymeric product of reaction is generally obtained as a solution. It can be isolated by evaporation of the solvent. For application as an oil repellent, the polymeric product is generally required in liquid form and the solution obtained by reaction can often be diluted to a solution suitable for application to textiles. Alternatively the polymeric product can be dissolved in a different solvent for application to textiles, for example in a polar organic solvent of higher boiling point. The polymeric product can alternatively be emulsified by mixing with water and an emulsifying agent, such as a cationic surfactant and/or a nonionic or anionic surfactant. The polymeric product can be isolated before emulsification or the reaction product solution can be emulsified, optionally with removal of solvent.

**[0025]** The solution or emulsion of polymeric product can be applied to fibrous substrates such as textiles by any of the methods known for treatment of textiles with liquids. The concentration of the polymeric product in the solution applied to the textile can for example be 0.5 to 20% by weight, preferably 1 to 5%. When the textile is a fabric, the fabric can be immersed in the solution or can be padded or sprayed with the solution. The treated textile is dried and is preferably heated, for example at 100-200°C, to develop the oil repellency.

**[0026]** The textile which is treated is preferably a fabric, including woven, knitted and nonwoven fabrics, fabrics in garment form and carpet, but can be a fibre or yarn or intermediate textile product such as a sliver or roving. The textile material can be a natural

fibre such as cotton or wool, a manmade fibre such as viscose rayon or lyocell or a synthetic fibre such as polyester, polyamide or acrylic fibre, or can be a mixture of fibres such as a mixture of natural and synthetic fibres. The polymeric product of the invention is particularly effective in rendering cellulosic fibres such as cotton or rayon oleophobic and oil repellent.

- 5 The process of the invention generally also renders the textile hydrophobic and water repellent. Fabric treatment with the polymeric product of the invention imparts oil repellency to fabrics whilst at the same time imparting an improvement in feel compared to untreated fabric and also imparting an improvement in feel compared to fabric treated with an unmodified fluoropolymer textile treatment agent such as polymer (B) used alone.

10 [0027] The fibrous substrate can alternatively be leather. The polymeric product can be applied to leather from aqueous solution or emulsion at various stages of leather processing, for example during leather wet end processing or during leather finishing, to render the leather hydrophobic and / or oleophobic.

15 [0028] The fibrous substrate can alternatively be paper. The polymeric product can be applied to preformed paper or at various stages of papermaking, for example during drying of the paper.

20 [0029] The invention is illustrated by the following Examples

#### Evaluation on Textile Fabrics

##### Example 1

25 [0030] To a three necked round bottomed flask were charged  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_2\text{C}_8\text{F}_{17}$  (Monomer FM) (24g), stearyl acrylate (10g) and glycidyl methacrylate (6g). To this was added butan-1-ol (30g) and xylene (30g) followed by AIVN (0.6g). The reaction mixture was heated to 90°C under a stream of nitrogen and held at this  
30 temperature for 150 minutes, upon which an aminofunctional siloxane  $\text{H}_2\text{N}(\text{CH}_2)_3\text{SiMe}_2\text{O}(\text{SiMe}_2\text{O})_{10}\text{SiMe}_2(\text{CH}_2)_3\text{NH}_2$  (20g) dissolved in 2-butanone (20g) was

added. The reaction mixture was then held at 90°C for a further four hours to yield a solution of a siloxane modified fluoro/organic polymeric product.

### Example 2

5

[0031] To a three necked round bottomed flask were charged Monomer FM (24g), stearyl acrylate (10g) and glycidyl methacrylate (6g). To this was added butan-1-ol (30g) and xylene (30g) followed by AIVN (0.6g). The reaction mixture was heated to 90°C under a stream of nitrogen and held at this temperature for 150 minutes, upon which an


10 aminofunctional siloxane  $\text{H}_2\text{N}(\text{CH}_2)_3\text{SiMe}_2\text{O}(\text{SiMe}_2\text{O})_{50}\text{SiMe}_2(\text{CH}_2)_3\text{NH}_2$  (20g) dissolved in 2-butanone (20g) was added. The reaction mixture was then held at 90°C for a further four hours to yield a solution of a siloxane modified fluoro/organic polymeric product.

### Example 3

15

[0032] To a three necked round bottomed flask were charged fluoromethacrylate monomer (24g), stearyl acrylate (10g) and glycidyl methacrylate (6g). To this was added butan-1-ol (30g) and xylene (30g) followed by AIVN (0.6g). The reaction mixture was heated to 90°C under a stream of nitrogen and held at this temperature for 150 minutes, upon which an

20 aminofunctional siloxane of general structure




[I]

(20g – 0.38 % by weight Nitrogen) dissolved in 2-butanone (20g) was added. The reaction  
25 mixture was then held at 90°C for a further four hours to yield a solution of a siloxane modified fluoro/organic polymeric product.

Example 4

[0033] To a three necked round bottomed flask were charged fluoromethacrylate monomer (24g), stearyl acrylate (10g) and glycidyl methacrylate (6g). To this was added butan-1-ol (30g) and xylene (30g) followed by AIVN (0.6g). The reaction mixture was heated to 90°C under a stream of nitrogen and held at this temperature for 150 minutes, upon which an aminofunctional siloxane of general structure



(R is a mixture of linear and branched hydrocarbons C13)

[III]

(20g – 0.41% by weight Nitrogen) dissolved in 2-butanone (20g) was added. The reaction mixture was then held at 90°C for a further four hours to yield a solution of a siloxane modified fluoro/organic polymeric product.

15 Reference Example C1

[0034] To a three necked round bottomed flask were charged fluoromethacrylate monomer (24g) and stearyl acrylate (10g). To this was added butan-1-ol (30g) and xylene (30g) followed by AIVN (0.6g). The reaction mixture was heated to 90°C under a stream of nitrogen and held at this temperature for 150 minutes to yield a solution of a fluoro/organic co-polymer.

Comparative Tests

[0035] The oil-repellency and water repellency of the fluorsilicone samples were evaluated on cotton weave and cotton polyester weave fabric. The oil repellency was carried out using the AATCC 118-1992 test method and the water repellency was evaluated using the spray test AATCC 22-1989. The results are summarized in tables one and two.

Table 1: Oil repellency data for cotton and cotton polyester weave fabrics.

	<b>Cotton</b>	<b>Cotton/PE</b>
Example 1	5	5
Example 2	5	5
Example 3	5	5
Example 4	5	5
Reference C1	5	5

5 Table 2: Water repellency data for cotton and cotton polyester weave fabrics.

	<b>Cotton</b>	<b>Cotton/PE</b>
Example 1	80	90
Example 2	80	90
Example 3	90	90
Example 4	90	90
Reference C1	80	90

[0036] The handle of the fabrics were also assessed for their softness/feel compared to the untreated fabric and given the following ratings relating to feel

- 10                      3 - Harsher than untreated fabric  
                           2 - Similar to untreated fabric  
                           1 - Improved softness compared with untreated fabric

The results are shown in Table 3 below

Table 3: Handle ratings for cotton and cotton polyester treated fabrics.

	<b>Handle rating Treated Cotton</b>	<b>Handle rating Treated Cotton/Polyester</b>
Example 1	1	1
Example 2	1	1
Example 3	1	1
Example 4	1	1
Reference C1	2/3	2/3

[0037] It can be seen from Table 3 that all the polymeric products of the Examples improved the softness and feel of the fabrics, whereas the unmodified fluoropolymer C1 did not improve the feel of the fabric and gave a handle that was perceived by some testers as harsher than untreated fabric.

Evaluation on Leather (Leather wet-end )

[0038] The fluorosilicone prepared in Example 4 was diluted in 2-butanone to a solids content of 10%w/w. The resulting solution was then dispersed in decamethylcyclpentasiloxane (D5 fluid) to yield a solids content for the fluorosilicone of 2%w/w. A sample of chrome tanned bovine leather (150 mm x 150 mm ) was immersed in the solution and then air dried for 24 hours to remove the solvent and D5 fluid.

[0039] - The water repellency of the treated bovine leather was then evaluated using the SATRA (Shoe and Allied Trades Research Association) Maeser test according to the SATRA PM 34 test method, which measures the number of flexes before water starts to penetrate through the leather sample. The leather was evaluated in comparison with untreated chrome tanned leather (control) and with leather treated with a 2% w/w solution of polydimethylsiloxane. The results are shown in Table 4 below. The accepted industry



standard is at least 40,000 Maeser flexes before sample failure. Number of flexes at failure is obtained by visual inspection of the sample. Noticing water transfer in the following forms is considered the point of failure:

- 5      i)      Water beads pushing through the sample and collecting on the flesh side with a high contact angle.
- ii)     Small or large damp areas appearing on the flesh side and increasing in size.
- iii)    Water rushing through the sample in large volumes and at a high rate.

10      Water absorbance = P  
         Water transmitted = M

Table 4

Sample Name	P <sub>10 000</sub>	M <sub>10 000</sub>	P <sub>100 000</sub>	M <sub>100 000</sub>	Number of flexes at failure
Example 4	5.06%	0.0g	11.36%	0.0g	100 000 +
Control	105%	2.562g	-	-	11
Polydimethylsiloxane	71.51%	0.4232g	-	-	5

15      [0040]      The test on the leather treated with the fluorosilicone prepared in Example 4 was stopped at 100,000 flexes, with very little water absorbance and no water transmittance.

#### Leather finishing

20      [0041]      A sample of chrome tanned bovine nubuck leather (240mm x 150mm) was treated with the fluorosilicone of Example 4 which had been dissolved in methylethylketone to give a solids content of 2% w/w. The fluorosilicone was sprayed onto the leather surface using a back and forth motion for each application. The water repellency of the treated

25      leather was evaluated using a mixture of water and ethanol (85:15 weight ratio) as reported in Table 5

Table 5

Time to absorb the droplet	Blank	Additive application after the fixation		
	No silicone	1 application	2 applications	3 applications
Nubuck	20 secs	> 10 mins*	> 10 mins*	> 10mins*

5 (\*) Drop evaporates without penetration into the leather

[0042] The oil repellency was tested using samples of olive oil and hexadecane, as reported in Table 6

10 Table 6.

Time to absorb the droplet	Blank	Additive application after the fixation		
		1 application	2 applications	3 applications
Olive oil	20 secs	> 10 mins*	> 10 mins*	> 10 mins*
Hexadecane	1 sec	> 10 mins*	> 10 mins*	> 10 mins*

(\*) The droplet beads with no staining or spotting of the leather surface

# CLAIMS

1. A polymeric product having oil repellent properties comprising an amino-functional polysiloxane (A) bonded through its amino groups to an addition copolymer (B) of (B1) a fluoro-substituted alkyl ester of an olefinically unsaturated carboxylic acid and (B2) an olefinically unsaturated monomer having a functional group capable of reacting with the amino groups of polysiloxane (A) and optionally (B3) one or more olefinically unsaturated comonomers.
2. A polymeric product according to Claim 1 characterised in that the amino-functional polysiloxane (A) is a polydiorganosiloxane containing aminoalkyl groups of the formula  $R-(NH-A')_q-NH-A-$  attached to silicon, wherein A and A' are each independently a linear or branched alkylene group having 1 to 6 carbon atoms;  $q = 0-4$ ; and R is hydrogen or an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms.
3. A polymeric product according to Claim 1 or Claim 2 characterised in that the fluoro-substituted alkyl ester monomer B1 is an acrylate or methacrylate ester of the formula  $CH_2=C(R'')COO-D-R_f$  or  $CH_2=C(R'')COO-R_f$  where  $R_f$  is a branched or linear fluoroalkyl group having 3 to 21 carbon atoms,  $R''$  is H or methyl, and D is a divalent organic group.
4. A polymeric product according to any of Claims 1 to 3 characterised in that the monomer B2 is a substituted alkyl acrylate or methacrylate ester wherein the substituent in the alkyl group is a functional group capable of reacting with the amino groups of polysiloxane (A).
5. A polymeric product according to any of Claims 1 to 4, characterised in that the amino-functional polysiloxane (A) is bonded to the copolymer (B) by  $-N(R)-CH_2-CHOH-$  linkages derived from reaction of the amino groups of

(A) with epoxide groups in the copolymer (B), where R is hydrogen or an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms.

6. A polymeric product according to any of Claims 1 to 5 characterised in that the functional group in monomer (B2) capable of reacting with the amino groups of polysiloxane (A) is an anhydride, lactone, imide, carboxylic acid group, isocyanate or blocked isocyanate.
7. A polymeric product according to any of Claims 1 to 6 characterised in that the copolymer (B) contains a comonomer (B3) which is an alkyl acrylate or methacrylate having 1 to 30 carbon atoms in the alkyl group.
8. A process for the preparation of a product having oil repellent properties characterised in that an amino-functional polysiloxane (A) is reacted with an addition copolymer (B) of (B1) a fluoro-substituted alkyl ester of an olefinically unsaturated carboxylic acid and (B2) an olefinically unsaturated monomer having a functional group capable of reacting with the amino groups of polysiloxane (A) and optionally (B3) one or more olefinically unsaturated comonomers.
9. A polymeric product having oil repellent properties prepared by the process of Claim 8.
10. A textile treatment composition comprising a polymeric product according to any of Claims 1 to 7 or 9.
11. A process for rendering a fabric hydrophobic and oleophobic characterised in that a polymeric product according to any of Claims 1 to 7 or 9 is applied to the textile fabric.

12. A process for rendering leather hydrophobic and oleophobic characterised in that a polymeric product according to any of Claims 1 to 7 or 9 is applied to the leather either during wet end processing or leather finishing.
13. A process for rendering paper hydrophobic and oleophobic characterised in that a polymeric product according to any of Claims 1 to 7 or 9 is applied to the paper.